

LGET 2

SKF Extreme Temperature, Extreme Condition Bearing Grease

SKF LGET 2 is a synthetic fluorinated oil based grease, using a PTFE thickener. It is especially suitable for applications at extremely high temperatures from 200 °C (390 °F) up to 260 °C (500 °F).

- Long life in aggressive environments such as very reactive areas with a presence of high purity gaseous oxygen and hexane
- Excellent oxidation resistance
- Good corrosion resistance
- Excellent water and steam resistance

Typical applications:

- Bakery equipment (ovens)
- Kiln truck wheels
- Load rollers in copying machines
- Wafer baking machines
- Textile dryers
- Film stretching tenders
- Electric motors running at extreme temperatures
- Emergency / hot fans
- Vacuum pumps



Important note:

LGET 2 is a fluorinated grease and is not compatible with other greases, oils and preservatives. Therefore, very thorough cleaning of bearings and systems is essential before applying fresh grease (except when reapplying LGET 2).

SKF

Technical data

Designation	LGFP 2/(pack size)		
DIN 51825 code	KFK2U-40	Corrosion protection	
NLGI consistency class	2	Emcor:	
Soap type	PTFE	– standard ISO 11007	1–1
Colour	Whitish cream	Water resistance	
Base oil type	Synthetic (fluorinated polyether)	DIN 51 807/1, 3 hrs at 90 °C	0 max.
Operating temperature range	–40 to +260 °C (–40 to +500 °F)	Oil separation	
Dropping point DIN ISO 2176	>300 °C (>570 °F)	DIN 51 817, 7 days at 40 °C, static, %	13 max. 30 hrs at 200 °C (390 °F)
Base oil viscosity		Copper corrosion	
40 °C, mm ² /s	400	DIN 51 811, 110 °C	1
100 °C, mm ² /s	38	Rolling bearing grease life	
Penetration DIN ISO 2137		ROF test	>700, 5 600 r/min.*
60 strokes, 10 ⁻¹ mm	265–295	L ₅₀ life at 10 000 r/min., hrs	at 220 °C (430 °F)
Mechanical stability		EP performance	
Roll stability, 50 hrs at 80 °C, 10 ⁻¹ mm	±30 max. 130 °C (265 °F)	4–ball test, welding load DIN 51350/4	8 000 min.
		Available pack sizes	50 g (25 ml) syringe 1 kg

* Typical value



SKF lubricants offer major competitive advantages:

- Designed and tested to outperform under real conditions
- Product data include specific test results enabling a better selection
- Strict quality control of every production batch help ensure consistent performance
- Quality control allows SKF to offer a five-year shelf-life* from the date of production



Production processes and raw materials vastly influence grease properties and performance. It is virtually impossible to select or compare greases based only on their composition. Therefore, performance tests are needed to provide crucial information. In over 100 years, SKF has accrued vast knowledge about the interaction of lubricants, materials and surfaces.



This knowledge has led SKF, in many cases, to set industry standards in bearing lubricant testing. Emcor, ROF, ROF+, V2F, R2F and Bequiet are just some of the multiple tests developed by SKF to assess the performance of lubricants under bearing operating conditions. Many of them are widely used by lubricant manufacturers worldwide.

* SKF LGFP 2 food grade grease offers a two-year shelf-life from the date of production

© SKF is a registered trademark of the SKF Group.

© SKF Group 2011

The contents of this publication are the copyright of the publisher and may not be reproduced (even extracts) unless prior written permission is granted. Every care has been taken to ensure the accuracy of the information contained in this publication but no liability can be accepted for any loss or damage whether direct, indirect or consequential arising out of the use of the information contained herein.

PUB MP/P8 12046 EN · July 2011

