

LGWA 2

SKF High Load, Extreme Pressure, Wide Temperature Range Bearing Grease

SKF LGWA 2 is a premium quality mineral oil based, lithium complex grease with extreme pressure (EP) performance. LGWA 2 is recommended for general industrial and automotive applications, when loads or temperatures exceed the range of general purpose greases.

- Excellent lubrication at peak temperatures up to 220 °C (430 °F) for short periods
- Protection of wheel bearings operating under severe conditions
- Effective lubrication in wet conditions
- Good water and corrosion resistance
- Excellent lubrication under high loads and low speeds

Typical applications:

- Wheel bearings in cars, trailers and trucks
- Washing machines
- Fan and electric motors



Technical data

Designation	LGWA 2/(pack size)	
DIN 51825 code	KP2N-30	
NLGI consistency class	2	
Soap type	Lithium complex	
Colour	Amber	
Base oil type	Mineral	
Operating temperature range	-30 to +140 °C (-20 to +285 °F)	
Dropping point DIN ISO 2176	>250 °C (>480 °F)	
Base oil viscosity		
40 °C, mm ² /s	185	
100 °C, mm ² /s	15	
Penetration DIN ISO 2137		
60 strokes, 10 ⁻¹ mm	265-295	
100 000 strokes, 10 ⁻¹ mm	+50 max. (325 max.)	
Mechanical stability		
Roll stability, 50 hrs at 80 °C, 10 ⁻¹ mm	+50 max. change	
V2F test	'M'	
Corrosion protection		
Emcor: - standard ISO 11007	0-0	
- water washout test	0-0*	
Water resistance	DIN 51 807/1, 3 hrs at 90 °C	1 max.
Oil separation	DIN 51 817, 7 days at 40 °C, static, %	1-5
Lubrication ability	R2F, running test B at 120 °C	Pass at 100 °C (210 °F)
Copper corrosion	DIN 51 811, 110 °C	2 max.
EP performance	Wear scar DIN 51350/5, 1 400 N, mm	1,6 max.
4-ball test, welding load DIN 51350/4, N		2 600 min.
Available pack sizes		35, 200 g tube 420 ml cartridge 1, 5, 18, 50, 180 kg SKF SYSTEM 24 (LAGD/TLSD), TLMR

* Typical value



SKF lubricants offer major competitive advantages:

- Designed and tested to outperform under real conditions
- Product data include specific test results enabling a better selection
- Strict quality control of every production batch help ensure consistent performance
- Quality control allows SKF to offer a five-year shelf-life* from the date of production



Production processes and raw materials vastly influence grease properties and performance. It is virtually impossible to select or compare greases based only on their composition. Therefore, performance tests are needed to provide crucial information. In over 100 years, SKF has accrued vast knowledge about the interaction of lubricants, materials and surfaces.



This knowledge has led SKF, in many cases, to set industry standards in bearing lubricant testing. Emcor, ROF, ROF+, V2F, R2F and Bequiet are just some of the multiple tests developed by SKF to assess the performance of lubricants under bearing operating conditions. Many of them are widely used by lubricant manufacturers worldwide.

* SKF LGFP 2 food grade grease offers a two-year shelf-life from the date of production

© SKF is a registered trademark of the SKF Group.

© SKF Group 2014

The contents of this publication are the copyright of the publisher and may not be reproduced (even extracts) unless prior written permission is granted. Every care has been taken to ensure the accuracy of the information contained in this publication but no liability can be accepted for any loss or damage whether direct, indirect or consequential arising out of the use of the information contained herein.

PUB MP/P8 12054 EN · January 2014

