

## LGWM 1

# SKF Extreme Pressure, Low Temperature Bearing Grease

SKF LGWM 1 is a low consistency mineral oil based grease, using a lithium soap and containing extreme pressure additives. It is extremely suitable for the lubrication of bearings operating under both radial and axial loads.

- Good oil film formation at low temperatures down to  $-30\text{ }^{\circ}\text{C}$  ( $-20\text{ }^{\circ}\text{F}$ )
- Good pumpability down to low temperatures
- Good corrosion protection
- Good water resistance

### Typical applications:

- Wind turbine main shafts
- Screw conveyors
- Centralised lubrication systems
- Spherical roller thrust bearing applications



## Technical data

Designation	LGWM 1/(pack size)		
DIN 51825 code	KP1G-30	<b>Water resistance</b>	
NLGI consistency class	1	DIN 51 807/1, 3 hrs at 90 °C	1 max.
Soap type	Lithium	<b>Oil separation</b>	
Colour	Brown	DIN 51 817, 7 days at 40 °C, static, %	8–13
Base oil type	Mineral	<b>Copper corrosion</b>	
Operating temperature range	–30 to +110 °C (–20 to +230 °F)	DIN 51 811, 110 °C	2 max. at 90 °C (>195 °F)
Dropping point DIN ISO 2176	>170 °C (>340 °F)	<b>EP performance</b>	
Base oil viscosity		Wear scar DIN 51350/5, 1 400 N, mm	1,8 max.
40 °C, mm <sup>2</sup> /s	200	4–ball test, welding load DIN 51350/4	3 200 min.*
100 °C, mm <sup>2</sup> /s	16	<b>Fretting corrosion</b>	
Penetration DIN ISO 2137		ASTM D4170 (mg)	5,5*
60 strokes, 10 <sup>-1</sup> mm	310–340	<b>Available pack sizes</b>	420 ml cartridge
100 000 strokes, 10 <sup>-1</sup> mm	+50 max.		5, 50, 180 kg
<b>Corrosion protection:</b>			
Emcor: – standard ISO 11007	0–0		
– water washout test	0–0		

\* Typical value



### SKF lubricants offer major competitive advantages:

- Designed and tested to outperform under real conditions
- Product data include specific test results enabling a better selection
- Strict quality control of every production batch help ensure consistent performance
- Quality control allows SKF to offer a five-year shelf-life\* from the date of production



Production processes and raw materials vastly influence grease properties and performance. It is virtually impossible to select or compare greases based only on their composition. Therefore, performance tests are needed to provide crucial information. In over 100 years, SKF has accrued vast knowledge about the interaction of lubricants, materials and surfaces.



This knowledge has led SKF, in many cases, to set industry standards in bearing lubricant testing. Emcor, ROF, ROF+, V2F, R2F and Bequiet are just some of the multiple tests developed by SKF to assess the performance of lubricants under bearing operating conditions. Many of them are widely used by lubricant manufacturers worldwide.

\* SKF LGFP 2 food grade grease offers a two-year shelf-life from the date of production

© SKF is a registered trademark of the SKF Group.

© SKF Group 2011

The contents of this publication are the copyright of the publisher and may not be reproduced (even extracts) unless prior written permission is granted. Every care has been taken to ensure the accuracy of the information contained in this publication but no liability can be accepted for any loss or damage whether direct, indirect or consequential arising out of the use of the information contained herein.

PUB MP/P8 12055 EN · July 2011

